

Recommendation on Chemical Resistance

Below protective gloves have been tested in accordance with EN 16523-1:2015+A1:2018 "Determination of material resistance to permeation by chemicals" and achieve following test results.

Caution: Damaged or swelling gloves shall be changed immediately!
For reason of precaution it is recommended to change gloves after 2 hours!

TEST RESULTS by:
• ProQares, Rijswijk, The Netherlands

Chemicals (synonyms)	Brand Name	sempercare® edition	sempercare® edition IC	sempercare® edition IC sterile	sempercare® premium	sempercare® latex powdered
	Cas-No. / Spec Code	LCF-050NA	LCT-059NA	LCT-059NA	LFF-063NA	LXS-050NA
Acetic acid (10%)	64-19-7	n/a	n/a	n/a	n/a	A
Acetone (2-propanone, methyl ketone)	67-64-1	X	X	X	X	X
Acetonitrile (cyanomethane, ethyl nitrile)	75-05-8	X	X	X	X	X
Benzalconiumchloride liquid (Quarts)	63449-41-2	n/a	Level 6	Level 6	n/a	Level 6
Chlorhexidindigluconat (20%)	18472-51-0	n/a	Level 6	Level 6	n/a	Level 6
Chloroform (99%) (trichlormethan)	67-66-3	X	X	X	X	X
Cyclohexanol (Hexalin / at 23°C)	108-93-0	X	X	X	X	X
Dichlormethan (Methylendichlorid, Freon 30)	75-09-2	X	X	X	X	X
Diethyl amine (DEA)	109-89-7	X	X	X	X	X
Diethyl ether (diethyloxid, ethoxyethane)	60-29-7	X	X	X	X	X
Dimethylsulfoxid DMSO (deltan, demasorb)	67-68-5	X	X	X	X	X
Ethanol (40%) (ethyl alcohol)	64-17-5	X	X	X	X	X
Ethanol (70%) (ethyl alcohol)	64-17-5	X	X	X	X	X
Ethanol (80%) (ethyl alcohol)	64-17-5	X	X	X	X	X
Ethanol (95%) (ethyl alcohol)	64-17-5	X	X	X	X	X
Ethidium bromide (1%) (homidium bromide)	1239-45-8	n/a	n/a	n/a	n/a	X
Ethyl acetate (Aceto acid ether)	141-78-6	X	X	X	X	X
Gasoline (Petrol, heavy, 150 - 190°C)	8032-32-4	X	X	X	X	X
Heptane - n	142-82-5	X	X	X	X	X
Hexane - n	110-54-3	X	X	X	X	X
Isopropyl alcohol (40%) (2-propanol, IPA)	67-63-0	n/a	A	A	n/a	A
Isopropyl alcohol (70%) (2-propanol, IPA)	67-63-0	n/a	n/a	n/a	n/a	X
Methanol p.a. (methyl alcohol)	67-56-1	X	X	X	X	X

Chemicals (synonyms)	Brand Name	sempercure® edition	sempercure® edition IC	sempercure® edition IC sterile	sempercure® premium	sempercure® latex powdered
	Cas-No. / Spec Code	LCF-050NA	LCT-059NA	LCT-059NA	LFF-063NA	LXS-050NA
Toluene (methylbenzol, phenylmethan, toluol)	108-88-3	X	X	X	X	X
Trichlorethane (methyltrichloromethane)	71-55-6	X	X	X	X	X
Xylene (xylo, dimethylbenzene)	95-47-6	X	X	X	X	X

X	Not Recommended	Level 3	> 60min
A	Splash Protection - change glove immediately after contact!	Level 4	> 120min
Level 1	> 10min	Level 5	> 240min
Level 2	> 30min	Level 6	> 480min

n/a not available

IMPORTANT NOTE: The latest chemical resistance list can be found at www.sempermed.com. Please note that the product characteristics are directly dependent on the conditions of use and on the purity of the chemical substances concerned. The chemical resistance has been assessed under laboratory conditions and cannot reflect all actual conditions. When working with materials that are harmful to the skin, please always inspect the glove for any holes or tears prior to use. In principle, tests and certificates may only be regarded as general indications and do not exempt the user from the responsibility of making sure that the glove affords the protection requirements for the intended purpose prior to use. The chemical resistance recommendations do not form part of the specifications.

CAUTION: Failure to observe this information, in particular with regard to (chemical) resistance, frequency of use and tolerability of the gloves, can result in personal injury and/or material damage. Semperit does not accept any liability for incorrect use of the gloves. In case of doubt, obtain expert advice before use.

This document was issued electronically and is therefore valid without signature and has a validity of up to one year.

Date: 31.01.2024